


Streamlined Treatment Option for Remediation of Commingled Perchlorate and Explosives in Groundwater

National Defense Industry Association 29th Environmental and Energy Symposium and Exhibition

April 8, 2003

David Hill (IAGWSP)
Scott Veenstra* (AMEC)
Katherine Weeks (AMEC)
A. Paul Tonga (Envirogen)





Innovative Technology Evaluation Team (ITE)

- Army National Guard
 - Ben Gregson, Dave Hill




- Army Corps of Engineers
 - ° Heather Sullivan, Ian Osgerby



- AMEC Earth and Environmental
 - ° Scott Veenstra, Katy Weeks



- 15,000 acres on Cape Cod
- Impact Area and Training Ranges used for target practice and range training operations since 1940s





ITE Mission

- Identify and evaluate innovative remediation technologies to address low levels of explosives and perchlorate contamination
- Recommend technologies for implementation at contaminated sites on Camp Edwards/MMR
- Support future application at other DoD/ARNG training installations





Fluidized Bed Reactor (FBR) Evaluation


- Can FBR systems remediate low concentrations of perchlorate?
- Can FBR systems concurrently degrade explosives as well as perchlorate?
- Can a single FBR replace traditional lead-lag arrangement of FBR and GAC?



Fluidized Bed Reactor (FBR)

Ex Situ Fluidized Bed Reactor (FBR) - Envirogen

- °Uses GAC as substrate for microbial growth
- °Demonstrated at Aerojet site in California





FBR Treatability Study – Set up

- Initial concentrations in groundwater were 190 ug/L RDX and 100 ug/L perchlorate
- Lab scale columns loaded with GAC
- FBR #1 fed acetic acid, a simple organic substrate
- FBR #2 fed molasses, a complex organic substrate
- FBR #3 was a control (no substrate or nutrients)
- Each column fed groundwater until perchlorate effluent concentrations approached influent concentrations meaning GAC saturated with perchlorate



FBR Treatability Study – Set up




 Photo courtesy of Envirogen



FBR Treatability Study – Phase 1

Phase 1 - Acclimation

- FBRs #1 and #2 inoculated with naturally occurring bacteria already acclimated to each of the nutrient substrates
- Inoculated to accelerate study
- Operated until acclimated for destruction of perchlorate as demonstrated by effluent < 5 ug/L



FBR Treatability Study – Phase 2

Phase 2 – Operation

- Operated at excess organic substrate feed rates for degradation of perchlorate and explosives
- Set at hydraulic retention time (HRT) of 80 minutes
- Operated for one month and achieved perchlorate effluent < 1.5 ug/L in FBR #1




FBR Treatability Study – Phase 3

Phase 3 – Improve System Performance

- Sustained FBR #1 perchlorate effluent < 1.5 ug/L
- Reduced organic feed rate by half
- Optimize for degradation of perchlorate and RDX




FBR Treatability Study Results





FBR Treatability Study Results





FBR Treatability Study Conclusions

- Success with acetic acid fed FBR (FBR #1)
- Field-equivalent HRT of 80 minutes
 - ° Perchlorate reduced from 100 ug/L < 1.5 ug/L</p>
 - ° RDX reduced from 190 ug/L to < 2 ug/L</p>
- HRT of 35 minutes
 - Perchlorate reduced to < 1.5 ug/L
 - ° RDX could be removed by secondary GAC unit



FBR Treatability Study Conclusions

- The molasses fed FBR (FBR #2) degraded perchlorate and RDX, but did not meet study performance goals
- RDX that sorbed to the GAC in FBR #1 (acetic acid) was consistently 2 orders of magnitude lower than in FBR #2 and FBR #3 (control). This tells us that the biologically active film on the GAC in FBR #1 was effective at destroying a significant amount of sorbed RDX
- Bottom line = FBR can perform as a stand alone alternative to traditional lead-lag multiple step treatment trains for perchlorate and explosives



ITE - Moving Forward

- Results support design of treatment systems for concurrent removal of explosives and perchlorate
- Army/NGB considering FBR to treat commingled RDX and perchlorate in groundwater at Camp Edwards
- Potential application for the central portion of the groundwater plume underlying Demolition Area 1
- ITE team continues to evaluate GAC and IX Resins with respect to treatment of low concentrations of perchlorate and explosives in groundwater